



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 6 : C08K 3/34, C08F 2/44, C08K 7/10		A1	(11) International Publication Number: WO 99/47598
			(43) International Publication Date: 23 September 1999 (23.09.99)
(21) International Application Number: PCT/US99/05580		(74) Agent: STEVENS, Timothy, S.; Patent Dept., P.O. Box 1967, Midland, MI 48641-1967 (US).	
(22) International Filing Date: 16 March 1999 (16.03.99)			
(30) Priority Data: 60/078,085 16 March 1998 (16.03.98) US		(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).	
(71) Applicant (for all designated States except US): THE DOW CHEMICAL COMPANY [US/US]; 2030 Dow Center, Midland, MI 48674 (US).			
(72) Inventors; and			
(75) Inventors/Applicants (for US only): ALEXANDRE, Michael [BE/BE]; Rue de la Sablonniere 33, B-4031 Angleur (BE). DUBOIS, Philippe, G. [BE/BE]; Rue Grande 1, B-4260 Ciplat (BE). JEROME, Robert, J., E., G. [BE/BE]; Rue Alexandre Beaupain 4, B-4845 Sart-Jalhay (BE). GARCIA-MARTI, Miguel [ES/BE]; Jordaenslaan 24, B-8370 Blankenberge (BE). SUN, Tao [US/US]; 600 Foxboro Court, Midland, MI 48640 (US). GARCES, Juan, M. [US/US]; 1106 West Sugnet Street, Midland, MI 48640 (US). MILLAR, Dean, M. [US/US]; 1101 Adams Drive, Midland, MI 48640 (US). KUPERMAN, Alex [CA/US]; 903 Deerfield Court, Midland, MI 48640 (US).		Published With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.	

(54) Title: POLYOLEFIN NANOCOMPOSITES

(57) Abstract

The present invention is a nanocomposite which is a dispersion of nanofiller particles derived from layered metal oxides or metal oxide salts. The nanocomposite is advantageously prepared by first swelling an untreated clay in water, then removing the water to form an organophilic clay that is dispersible in non-polar organic solvents. The organophilic clay can then be treated with an alkyl aluminosilicate and subsequently a catalyst to form a complex that promotes olefin or styrenic polymerization and platelet dispersion. The nanocomposite can be prepared directly by *in situ* polymerization of the olefin or the styrene at the nanofiller particles without shear, without an ion exchange step, and without the need to incorporate polar substituents into the polyolefin or polystyrene.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LJ	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

POLYOLEFIN NANOCOMPOSITES

This invention relates to a dispersion of platelet particles in a polyolefin matrix, in particular, a dispersion prepared by *in situ* polymerization of the polyolefin.

Nanocomposites, which are dispersions of particles having at least one dimension that is less than 20 nm in a continuous polymer matrix, confer physical property enhancement to the polymer at a much lower particle content than conventional filled glass- or mineral-reinforced polymers. Nanocomposite materials are described in U.S. Patents 4,739,007; 4,618,528; 4,528,235; 4,874,728; 4,889,885; 4,810,734; 5,385,776; and 5,578,672; and in WO 93/11190.

Conventionally, these nanocomposites can be synthesized in a two-step process. In the first step, a clay or layered silicate is modified, generally by ion exchange of alkali metal or alkaline earth metal ions (which exist in natural forms of mica-type silicates) with organic cations such as alkyl ammonium silicates or suitably functionalized organosilanes. This modification step renders the normally hydrophilic mica-type silicate organophilic; the concomitant increase in the interlayer spacing between adjacent silicate layers enhances the dispersibility of the modified particles in a polymer matrix. In a second step, a melt-processible polymer and the organophilic particles are compatibilized under high shear to form a polymer with enhanced physical properties. Alternatively, a polymer that is generated *in situ* can react with functionalized groups in the organophilic particles.

Generally, relatively non-polar polymers such as polyolefins need to be copolymerized or grafted with a polar substituent such as maleic anhydride to facilitate the exfoliation of the multi-layered particles. (See *Macromolecules*, Vol. 30, p. 6333 (1997).) Without such modifications, the resultant composite will not have enhanced physical properties.

Composites of modified clays in polar-substituted polyolefins as described in the prior art suffer from a number of disadvantages. First, the ion exchange step is costly, time-consuming, and may introduce chemistries that degrade the physical properties of the final composite. Second, the modification of the polymer adds undesirable cost and may produce a more degradable polyolefin by virtue of the addition of oxygen to the polymer. Third, the use of high shear can cause undesirable polymer degradation.

In view of these disadvantages, it would be desirable to prepare polyolefin or polystyrene nanocomposites that do not require pretreatment of the clay or modification of the polymer or high shear processing.

5 The present invention addresses the aforementioned disadvantages by providing a nanocomposite comprising an *in situ* prepared polyolefin having dispersed therein nanofiller particles derived from metal layered oxides or metal oxide salts.

In a second aspect, the present invention is a method of preparing a nanocomposite comprising the steps of:

- a) dispersing a hydrophilic clay into water to swell the clay;
- 10 b) removing the water from the swelled clay to produce an organophilic clay;
- c) contacting the organophilic clay with an alkyl aluminosilane in the presence of an inert solvent for the organophilic clay and the alkyl aluminosilane to form a clay/alkyl aluminosilane complex;
- 15 d) contacting the complex with a catalyst that promotes olefin polymerization to form a clay/methyl aluminosilane/catalyst complex; and
- e) contacting the complex of step (d) with an olefin or a styrene monomer under polymerization conditions to form the nanocomposite.

In a third aspect, the present invention is a method of preparing a nanocomposite which comprises the steps of:

- 20 a) dispersing a hydrophilic smectite clay into water to swell the clay;
- b) removing the water from the swelled clay by freeze-drying to produce an organophilic clay;
- c) contacting the freeze-dried organophilic clay with an excess of methyl aluminosilane in the presence of an inert solvent for the organophilic clay and the methyl
- 25 aluminosilane to form a clay/methyl aluminosilane complex;
- d) removing the solvent and excess methyl aluminosilane from the complex;

e) contacting the complex of step (d) with a metallocene or Ziegler-Natta catalyst in the presence of a non-polar inert solvent to make a clay/methyl aluminoxane/catalyst complex; and

5 f) contacting the complex of step (e) with a ethylene or propylene under polymerization conditions to form the nanocomposite.

The present invention provides a way of preparing a polyolefin nanocomposite with enhanced physical properties that does not require either an ion exchange step or a polar group modified polymer. Moreover, the polyolefin nanocomposite can be prepared in the absence of shear.

10 The polyolefin nanocomposite of the present invention is advantageously prepared by first dispersing the multi-layered particles into water under such conditions to swell the particles. These multi-layered particles are preferably smectite clays such as montmorillonite, hectorite, saponite, sauconite, and vermiculite, or layered silicates such as magadiite and kenyaite. Other useful multi-layered particles include illite minerals and
15 layered aluminum or zirconium phosphates, as well as admixtures of the above-mentioned multi-layered particles.

The hydrophilic multi-layered particles are rendered organophilic by first swelling the particles in water, preferably hot deionized water, to form a gel-like slurry. It may be desirable to centrifuge or decant the slurry and discard any precipitate that is formed
20 before water is removed from the slurry.

Water may be removed, for example, by freeze-drying, distillation under reduced pressure, or distillation at ambient pressure, or a combination of these methods. The dehydrated multi-layered material is then advantageously dispersed in a non-polar inert solvent such as pentane, hexane, heptane, octane, and toluene, preferably at a
25 concentration of less than 10 weight percent based on the weight of the solvent and the treated clay.

An alkyl aluminoxane, preferably methyl aluminoxane (MAO), is then mixed with the dispersion of the dehydrated clay, generally as a substantially water-free solution in a non-polar inert solvent to form a MAO/treated clay complex. MAO is preferably added in
30 stoichiometric excess with respect to MAO-active sites in the dehydrated clay. Inasmuch as it is desirable to remove any unreacted MAO, the solution is preferably stripped of solvent and the resultant solid is preferably washed with a solvent for the MAO such as

toluene or xylene, to remove substantially all of the unreacted MAO. As used herein, the term "unreacted MAO" refers to the MAO that can be removed from the solid complex by solvent washing.

5 The MAO/dehydrated clay complex that is substantially free of unreacted MAO is advantageously redispersed in a solvent along with a catalyst that promotes polymerization of α -olefins or styrenes. Such catalysts include Ziegler-Natta catalysts and monocyclopentadienyl complexes biscyclopentadienyl complexes, ansa-metallocenes, and indenyl-fluorenyl substituted metallocenes such as those well known in the art. (See U.S. Patents 3,645,922; 5,064,802; 5,374,696, and 5,470,993.) The
10 MAO/dehydrated clay complex/catalyst dispersion is then contacted with an α -olefin, an α,ω -diolefin, a non-conjugated α -internal double bond diolefin, or a styrene monomer under polymerization conditions to form a polyolefin or a polystyrene nanocomposite. Examples of suitable monomers and/or comonomers include ethylene, propylene, 1-butene, 4-methyl-1-pentene, 1-hexene, 1-octene, 1-decene, styrene, ethylene-propylene-
15 diene monomer, 1,4-hexadiene, 1,5-hexadiene, 1,7-octadiene, 1,9-decadiene, dicyclopentadiene, ethylidene norbornene, and combinations thereof. The composite contains dispersed nanofiller particles within a polymer matrix.

The polyolefin is preferably substantially free of polar substituents, and more preferably contains no polar substituents. As used herein, the term "polar substituent"
20 refers to any substituent that increases the polarity of the polyolefin or polystyrene. Examples of such substituents include carboxylic acid groups, anhydride groups, silyl groups, and hydroxy groups. As used herein, the term "substantial absence" refers to less than about 1 percent, more preferably less than about 0.1 percent, and most preferably less than about 0.01 percent, based on the weight of the polymer.

25 The concentration of the dispersed particles in the polymer matrix is preferably not greater than about 10 percent, more preferably not greater than about 5 percent by volume, and preferably not less than about 0.5 percent, more preferably not less than about 1 percent by volume.

30 The polyolefin nanocomposite of the present invention has improved properties such as yield stress or stress at break over conventional polyolefins. Such improvements result in a composite material that can be used to make molded parts.

The following examples are for illustrative purposes only and is not intended to limit the scope of this invention.

Example 1

Montmorillonite (40 g, Crook County, Wyoming, USA) and deionized water (1 liter) were stirred together in a flask at 80°C for 2 hours. The resultant gel-like slurry was centrifuged for 30 minutes at 2000 rpm. A precipitate that formed during centrifugation was discarded, and the filtrate was split into two 1-liter flasks, both of which were placed into a Labconco Freeze-dryer 8 (Labconco Corporation, Kansas City, MO) to remove water under vacuum. After removal of water from the frozen filtrate, a fluffy white solid was obtained.

A portion of this resulting solid (2.5 g) was further degassed at 105°C under vacuum overnight. The degassed solid was dispersed in 300 mL of freshly distilled and dried heptane under agitation and without exposure to air. A solution of MAO in toluene (Witco, Corporation, 25 mL of a 1.65 M solution) was placed in a flask and heated to 50°C to evaporate the toluene and the residual trimethylaluminum. The resultant dry MAO was redissolved in 25 mL of freshly dried toluene. The MAO solution was transferred to the freeze-dried clay/heptane slurry with stirring at 50°C. Heating continued for 1 hour, whereupon the solvent was removed under vacuum at 50°C. The resultant powder was heated to 150°C for 2 hours, then cooled to room temperature. The powder was washed three times with freshly dried toluene (3 x 150 mL at 80°C) to remove excess MAO, and dispersed with stirring in freshly dried heptane (250 mL).

A portion of the MAO/dehydrated clay/heptane slurry (100 mL) was transferred into a 200-mL round-bottom flask and heated to 80°C with stirring. Then, the catalyst (*t*-butylamido) dimethyl (tetramethyl- η^5 -cyclopentadienyl)silane titanium dimethyl (The Dow Chemical Company, 1 mL of 4.55×10^{-3} M in heptane) was added to the slurry to form a yellowish slurry (presumably an activated clay catalyst slurry). The slurry was aged at 80°C for 1 hour, then transferred to a flame-dried 200-mL round-bottom flask for ethylene polymerization.

Ethylene was added to the activated clay catalyst slurry at 70°C and a pressure of 172 kP (1.7 atmospheres or 25 pounds per square inch gauge). The consumption of ethylene was monitored using a thermal conductivity flow meter. During the course of polymerization, the polymer-loaded clay particles were well dispersed in the reaction

solvent, and no composite settlement was observed. Removal of solvent after 6 hours of reaction resulted in 35 g of polyethylene-clay filler composite, which was a free-flowing powder. This powder was compressed into a disc and then into a film that was transparent to visible light. A Scanning Transmission Electron Microscopy image of the clay filled composite showed nanoscale clay particles uniformly dispersed in the polyethylene matrix.

Example 2

The procedure of Example 1 is repeated but with the myriad of variations as set forth in Table I.

Table I

Sample	Filler	State	Mass of filler ^{a)} (g)	MAO 10 ⁻³ mole	Catalyst 10 ⁻⁶ mole	Al/Ti initial ratio	Filler loading (wt%)
LD-21	ma	uncalcined	0.5	8.25	2.6	3170	-
LD-22	ma	uncalcined	0.5	8.25	5.21	1580	-
LD-23	mo	calcined	0.5	8.25	2.6	3170	-
LD-25	none	-	-	24.75	15.63	1580	0
LD-26	h	uncalcined	3	33	15.63	2110	4.2
LD-27	mo	uncalcined	2.44	27.22	12.5	2180	3.3
LD-29	h	uncalcined	2.55	19.8	13.66	1450	3.8
LD-31	h	uncalcined	2.55	19.8	13.66	1450	4.0
LD-32	mo	uncalcined	2.55	19.8	13.66	1450	3.9
LD-33	mo	uncalcined	2.55	19.8	13.66	1450	4.1
LD-34	h	uncalcined	2	15.5	10.63	1450	18.2
LD-35	k	calcined	3.05	23.76	16.19	1470	2.3
LD-36	h	uncalcined	3.06	23.76	16.19	1470	3.4
LD-36A	h	uncalcined	3.06	23.76	16.19	1470	-
LD-36B	h	uncalcined	3.06	23.76	16.19	1470	-
LD-36C	h	uncalcined	3.06	23.76	30.75	770	4.5
LD-36D	h	uncalcined	3.06	23.76	30.75	770	13.0
LD-36E	h	uncalcined	3.06	23.76	30.75	770	2.8
LD-36F	h	uncalcined	3.06	33	30.75	1075	11.4
LD-37	mal	uncalcined	3.06	23.76	30.75	770	4.6
LD-38	ma2	uncalcined	3.06	16.5	30.75	535	-

k = kaolin, h = hectorite, mo = montmorillonite, ma = magadiite (first lot), mal = magadiite (Na⁺H⁺), ma2 = magadiite (H⁺)

a) initial weight before drying

0.3 bar H₂ added during polymerization of Samples LD-36 to LD-38

It should be noted that Sample LD-35 is a "microcomposite" and not, strictly speaking, a "nanocomposite". It should also be noted that Sample LD-25 is not a "nanocomposite" but instead is a control, i.e., no filler added. Hydrogen is added during the polymerization of Samples LD-36 to LD-38. Such addition of hydrogen reduces the molecular weight of the polymer by chain transfer, i.e., hydrogen is a chain transfer agent and in the broad aspect of the instant invention, any suitable chain transfer agent can be used. Table II lists the activity of the catalyst in the polymerization for most of the Samples of Table I, which activity is expressed in terms of kilograms of polymer produced per gram of catalyst used.

Table II

Nanocomposite	Activity	Nanocomposite	Activity
LD 25 (HDPE)	50	LD 35 (kaolin)	89
LD 26 (hectorite)	5.19	LD 36 (hectorite)	49.4
LD 27 (mont.)	164.7	LD 36C (hectorite)	40.9
LD 29 (hectorite)	129.5	LD 36D (hectorite)	21.6
LD 31 (hectorite)	108.0	LD 36E (hectorite)	56.9
LD 32 (mont.)	178.0	LD 36F (hectorite)	<7.4
LD 33 (mont.)	102.4	LD 37 (magadiite Na ⁺ /H ⁺)	145.3

Table III lists various tensile testing for many of the Samples of Table I at a strain rate of 1.25 per minute. The data in Table III show that the Samples polymerized with the addition of hydrogen have a surprising combination of both high modulus and high strain at break.

Table III

		Young's Modulus (MP)	% Strain at break	Stress at Yield (kP)	Stress at break (kP)
LD-25		960	496	21000	27200
	Std. Dev.	130	138	1530	5500
LD-26		620	228	(no yield)	36400
	Std. Dev.	3.7	16		3000
LD-27		645	231	(no yield)	36500
	Std. Dev.	56	24		3535
LD-29		910	287	(no yield)	49264
	Std. Dev.	74	26		3569
LD-31		930	263	(no yield)	47507
	Std. Dev.	100	55		6931
LD-32		590	284	(no yield)	48347
	Std. Dev.	290	14		24652
LD-33		770	227	(no yield)	46680
	Std. Dev.	45	19		1709
LD-35		590	353	(no yield)	58124
	Std. Dev.	35	34		6070
LD-36		2520	684	29800	39328
	Std. Dev.	195	94	283	8626
LD-36C		1800	697	26451	44565
	Std. Dev.	160	10	634	1288
LD-36C (repeat)		1600	658	26000	39053
	Std. Dev.	320	41	517	5891

CLAIMS:

1. A nanocomposite comprising an *in situ* prepared polyolefin having dispersed therein nanofiller particles derived from metal layered oxides or metal oxide salts.

5 2. The nanocomposite of Claim 1 wherein the polyolefin is a polymer of ethylene, propylene, 1-pentene, 1-butene, 4-methyl-1-pentene, 1-hexene, 1-octene, 1-decene, styrene, ethylidene norbornene, 1,4-hexadiene, 1,5-hexadiene, 1,7-octadiene, 1,9-decadiene, dicyclopentadiene, or ethylene-propylene-diene monomer; or copolymers thereof.

10 3. The nanocomposite of Claim 1 wherein the polyolefin is a polymer of ethylene or propylene, and wherein the volume percent of nanofiller particles dispersed in the ethylene or the propylene is in the range of 1 to 10 percent.

4. A method of preparing a nanocomposite comprising the steps of:

a) dispersing a hydrophilic clay into water to swell the clay;

15 b) removing the water from the swelled clay to produce an organophilic clay;

c) contacting the organophilic clay with an alkyl aluminosilicate in the presence of an inert solvent for the organophilic clay and the alkyl aluminosilicate to form a clay/alkyl aluminosilicate complex;

20 d) contacting the complex with a catalyst that promotes olefin polymerization to form a clay/alkyl aluminosilicate/catalyst complex; and

e) contacting the complex of step (d) with an olefin monomer under polymerization conditions to form the nanocomposite.

5 5. The method of Claim 4 wherein the clay is sodium montmorillonite, laponite, or hectorite.

25 6. The method of Claim 5 wherein water is removed by freeze-drying.

7. The method of Claim 6 wherein the catalyst is a Ziegler-Natta catalyst or a metallocene catalyst.

8. A method of preparing a nanocomposite comprising the steps of:

a) dispersing a hydrophilic smectite clay containing alkali metal or alkaline earth metal cations into water to swell the clay;

b) removing the water from the swelled clay by freeze-drying to produce an organophilic clay;

c) contacting the freeze-dried organophilic clay with an excess of methyl aluminoxane in the presence of an inert solvent for the organophilic clay and the methyl aluminoxane to form a clay/methyl aluminoxane complex;

d) removing the solvent and excess methyl aluminoxane from the complex;

e) contacting the complex of step (d) with a metallocene or Ziegler-Natta catalyst in the presence of a non-polar inert solvent to make a clay/methyl aluminoxane/catalyst complex; and

f) contacting the complex of step (e) with a ethylene or propylene under polymerization conditions to form the nanocomposite.

9. The method of Claim 8 wherein the smectite clay is sodium montmorillonite.

10. The method of Claim 4 further including adding a chain transfer agent during step (e).

11. The method of Claim 10 where the chain transfer agent is hydrogen.

12. The method of Claim 8 further including adding a chain transfer agent during step (f).

13. The method of Claim 12 where the chain transfer agent is hydrogen.

14. The nanocomposite of Claim 1 wherein the percent strain at break is greater than five hundred percent and the tensile modulus is greater than one thousand five hundred MP.

15. The nanocomposite of Claim 1 wherein the percent strain at break is greater than six hundred percent and the tensile modulus is greater than one thousand eight hundred MP.

INTERNATIONAL SEARCH REPORT

Int. appl. No.
PCT/US 05580

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C08K3/34 C08F2/44 C08K7/10

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C08K C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the International search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 4 618 528 A (SACKS WILLIAM ET AL) 21 October 1986 (1986-10-21) cited in the application table 5	1-3, 14, 15
E	US 5 910 523 A (HUDSON STEVEN DAVID) 8 June 1999 (1999-06-08) the whole document	1-3, 14
X	WO 93 04118 A (ALLIED SIGNAL INC) 4 March 1993 (1993-03-04) table 11	1-3, 14
X	WO 95 06090 A (ALLIED SIGNAL INC) 2 March 1995 (1995-03-02) page 28, paragraph 1 page 29, line 35 - line 38	1-3, 14
-/-		

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

28 July 1999

Date of mailing of the international search report

05/08/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo rd,
Fax: (+31-70) 340-3016

Authorized officer

Andriollo, G

INTERNATIONAL SEARCH REPORT

Inten no Publication No
PCT/US /05580

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
------------	--	-----------------------

P,X	WO 98 53000 A (EXXON CHEMICAL PATENTS INC) 26 November 1998 (1998-11-26) claims 1-5	1,14
-----	---	------

P,X	US 5 866 645 A (SHI HENG-ZHEN ET AL) 2 February 1999 (1999-02-02) claims 2,5,46	1
-----	---	---

A	WO 97 00910 A (EXXON RESEARCH ENGINEERING CO) 9 January 1997 (1997-01-09) claims 1-3; table 2	1
---	---	---

INTERNATIONAL SEARCH REPORT

...formal patent family members

Intern. Application No
PCT/US 98/05580

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 4618528	A	21-10-1986	US 4528235 A	09-07-1985
			US 4728478 A	01-03-1988
US 5910523	A	08-06-1999	NONE	
WO 9304118	A	04-03-1993	AT 159270 T	15-11-1997
			CA 2115255 A	04-03-1993
			DE 69222773 D	20-11-1997
			DE 69222773 T	12-02-1998
			EP 0598836 A	01-06-1994
			JP 2674720 B	12-11-1997
			JP 6504810 T	02-06-1994
			WO 9304117 A	04-03-1993
			US 5747560 A	05-05-1998
WO 9506090	A	02-03-1995	US 5514734 A	07-05-1996
WO 9853000	A	26-11-1998	NONE	
US 5866645	A	02-02-1999	NONE	
WO 9700910	A	09-01-1997	AU 705183 B	20-05-1999
			AU 5798396 A	22-01-1997
			CA 2221649 A	09-01-1997
			CN 1199413 A	18-11-1998
			EP 0833863 A	08-04-1998
			NO 976007 A	20-02-1998
			PL 328865 A	01-03-1999
			US 5883173 A	16-03-1999

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☒ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.